FLUIGLIDE "E"

PAGE 1 OF 2

THIS INFORMATION IS FOR THE USE OF CORROCOAT PERSONNEL & DISTRIBUTORS ONLY

TYPE: A cold cured 100% solids epoxide, specially modified to

give a low roughness amplitude with poor wet out

properties.

SUGGESTED USE: The purpose of Fluiglide 'E' is to offer a smooth uninterrupted

surface, increasing flow in the boundary layer whilst affording

some degree of resistance to abrasion.

LIMITATIONS: Fluiglide 'E' does not give the same performance as Fluiglide but

is able to withstand more arduous service conditions. The

upper temperature limit is 100°C.

HEALTH & SAFETY: Safety precautions should be observed when handling this

material. Skin contact should be avoided and eye protection, gloves and protective clothing worn. Sensitisation of the skin may occur if these precautions are not observed, otherwise this material is safe in use provided normal precautions for epoxy

resins are observed.

SURFACE PREPARATION: The surface should be prepared by grit blasting to Swedish

Standard SA3 with an ideal profile of around 75 microns.

APPLICATION EQUIPMENT: Brush.

APPLICATION: Fluiglide 'E' may be applied direct to the substrate except in the

case of concrete. The material should be applied in at least two coats of between 250 to 350 microns with a minimum d.f.t. of 500 microns. Where build up of damaged components is required this should be carried out first using Corrocoat EA and EB. Fluiglide 'E' should then be applied as a top coat to these products. Care should be taken to observe overcoating times and application during periods of high humidity (in excess of 85% RH) should be avoided. Where this material is used in a potable water environment, allow 7 days at and above 18°C prior to service. Fluiglide 'E' is approved for use for factory

applied products.

MIXING RATIO: 2:1 Base to Activator by weight.

MIXING: Weigh out 2 parts of Fluiglide 'E' base (white colour) to 1 part

of Fluiglide 'E' activator (straw coloured liquid) by weight. Thoroughly mix the two components with a suitable implement, preferably by power stirring until the material is an even colour

containing no streaks of unmixed material.

Corrocoat Limited, Forster Street, Leeds LS10 1PW. Tel: (0113) 276 0760. Fax: (0113) 2760700

Valid From: 18th December 2007 © COPYRIGHT 4/05 B

FLUIGLIDE

FLUIGLIDE "E"

PAGE 2 OF 2

POT LIFE: At 20°C Fluiglide 'E' is usable for approximately 30 minutes with

a gel time of 45 minutes. As temperature increases pot life

reduces but cold temperatures will extend pot life.

PACKAGING: 5 litre composite kits

STORAGE LIFE: 2 years minimum in unopened tins, stored at 5°C-40°C.

COLOUR AVAILABILITY: White. Dye should not be used with this product.

RECOMMENDED DFT: Minimum of 500 microns in two coats.

PRACTICAL SPREADING RATE: 0.6 litres/m² at 500 microns dft.

Note: This information is given in good faith but may increase dependent upon environment conditions, the geometry and nature of work undertaken and the skill and care of application. Corrocoat accept no responsibility for any deviation from these

values.

VOLUME SOLIDS: 100% solvent free.

SPECIFIC GRAVITY: 1.14

FLASH POINT: 95°C

TEMPERATURE LIMITS: Upper: 100°C (dependent upon environment)

Lower: No known limit.

ACTIVATOR TYPE: Aliphatic Polyamide.

OVERCOATING TIME: At 20°C minimum 4 hours, maximum 30 hours.

CURE TIME: Minimum service time 36 hours

Potable water 7 days at 18°C.

CLEANING SOLVENT: Acetone, methyl ethyl ketone, methyl iso butyl ketone, or

toluene before gel.

NOTE: DESIGN PARAMETERS SHOULD BE TAKEN INTO ACCOUNT WHEN USING THIS

MATERIAL TO INCREASE PUMP EFFICIENCIES. MAXIMUM BENEFIT CAN ONLY BE OBTAINED BY KEEPING COATING THICKNESS TO MINIMUM RECOMMENDATION. SOME ITEMS WITH NARROW PASSAGEWAYS WILL NOT

BENEFIT FROM THE APPLICATION OF THIS MATERIAL.

WHERE DOUBT EXISTS - SEEK ADVICE

Reviewed 12/2007 Reviewed 06/2011 Reviewed 07/2011 Reviewed 06/2012 Reviewed 02/2014 (No change) Reviewed 11/2016 Revised 05/2018